Scanning Tunneling Spectroscopic Studies of the Pairing Potential and Pairing Symmetry of Highly Dense MgB<sub>2</sub> N.-C. YEH, C.-T. CHEN, P. SENEOR, Dept. of Physics, California Institute of Technology, Pasadena, CA; R. P. VASQUEZ, Jet Propulsion Laboratory, Pasadena, CA; C. U. JUNG, Min-Seok PARK, Heon-Jung KIM, Sung-Ik LEE, Pohang Univ. of Science and Technology, Pohang, Korea -- Spatially resolved quasiparticle tunneling spectra on highly dense  $MgB_2$  pellets with  $T_c = 39$  K are taken using a low-temperature STM. The spectra on the as-grown samples reveal long-range spatial homogeneity (> 400 nm) within each grain, and macroscopic scale variations at length scales beyond a few µm's. The (dI/dV)-vs.-V spectra are insensitive to the tunneling impedance, and are consistent with a pairing potential  $\Delta$  ranging from 4.0 to 6.5 meV at 4.2 K. The universally pronounced V-shape spectra with vanishing density of states near the Fermi level do not agree well with BCS s-wave pairing, even if the effect of disorder is taken into account. Further BTK analysis based on the scenarios of anisotropic s-wave pairing and other pairing symmetries are considered and compared with the data. Tunneling spectra on etched MgB<sub>2</sub> samples that are free of surface carbonates and oxides according to the XPS studies are also taken and compared with those of as-grown MgB<sub>2</sub>.